

This Page Is Inserted by IFW Operations  
and is not a part of the Official Record

## **BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning documents *will not* correct images,  
please do not report the images to the  
Image Problem Mailbox.**



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)


(51) International Patent Classification <sup>6</sup> : <b>C12N 15/87, 15/88, A61K 9/50</b>		<b>A1</b>	(11) International Publication Number: <b>WO 96/00295</b>
			(43) International Publication Date: <b>4 January 1996 (04.01.96)</b>
(21) International Application Number: <b>PCT/US95/07857</b>		(81) Designated States: AM, AT, AU, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LT, LU, LV, MD, MG, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TT, UA, UG, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG), ARIPO patent (KE, MW, SD, SZ, UG).	
(22) International Filing Date: <b>23 June 1995 (23.06.95)</b>			
(30) Priority Data: <b>08/265,966 27 June 1994 (27.06.94) US</b>			
(71) Applicant: <b>THE JOHNS HOPKINS UNIVERSITY [US/US];</b> <b>720 Rutland Avenue, Baltimore, MD 21205 (US).</b>			
(72) Inventors: <b>TRUONG, Vu, L.; 2008 McElderry Street, Baltimore, MD 21205 (US). AUGUST, Thomas; 905 Poplar Hill Road, Baltimore, MD 21210 (US). LEONG, Kam, W.; 10242 Breconshire Road, Ellicott City, MD 21042 (US).</b>			
(74) Agents: <b>HOSCHETT, Dale et al.; Berner &amp; Allegretti, Ltd., Suite 1100, 1001 G Street, N.W., Washington, DC 20001-4597 (US).</b>			
		Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>	

(54) Title: **TARGETED GENE DELIVERY SYSTEM**

## (57) Abstract

A target-specific gene delivery system is made of enzymatically degradable gelatin and nucleic acids (DNA or RNA) microparticles with a linking moiety or a targeting ligand attached to the surface. The delivery system can be made by a simple method. Targeting ligands can be attached to the microparticle directly or via a linking moiety. The linkage design allows the attachment of any molecule onto the microparticle surface including antibodies, cell adhesion molecules, hormones and other cell-specific ligands.

## Synthesis of Gelatin-Plasmid DNA Microparticles



\* Circular, supercoiled double stranded plasmid cDNA 6.8kb (LAMP-1) or 5.1kb (Lactoferrin) 0.6-3.5 ug/ml in H<sub>2</sub>O.

\*\* gelatin (50 bloom, Type A from porcine skin) freshly made.

*FOR THE PURPOSES OF INFORMATION ONLY*

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

## TARGETED GENE DELIVERY SYSTEM

### BACKGROUND OF THE INVENTION

A variety of techniques have been used to introduce foreign genes into cells. Physical methods include co-precipitation with calcium phosphate, electroporation, and particle bombardment. While these direct transfer techniques are adequate *in vitro*, they are impractical *in vivo*. Promising *in vivo* gene therapy relies on a carrier such as viral vectors or liposomes for delivery. There are still lingering safety concerns for viral vectors. Another limitation is the size of the DNA sequences, usually limited to 7-8 kb, that can be incorporated into the viral vector. Liposomes, on the other hand, have low loading level in general. In both cases, there is the issue of cell or tissue specificity for these gene delivery systems.

Controlled drug delivery has significantly improved the success of many drug therapies (Langer, R., 1990, New methods of drug delivery, *Science*, 249:1527-33; Poznansky, et al., 1984, Biological approaches to the controlled delivery of drugs: a critical review, *Pharmacol. Rev.*, 36:277-336). A major goal of drug delivery is to localize the drug to the target site. These targeted-delivery systems often take the form of injectables composed of liposomes (Gregoriadis,

G., 1988, *Liposomes as Drug Carriers*, New York: Wiley; Litzinger, et al., 1992, Phosphatidylethanolamine liposomes: drug delivery, gene transfer and immunodiagnostic applications, *Biochimica et Biophysica Acta.*, 1113:201-27) and microspheres made of proteins (Cummings, et al., 1991, Covalent coupling of doxorubicin in protein microspheres is a major determinant of tumor drug deposition, *Biochem. Pharm.*, 41:1849-54; Verrijk, et al., 1991, Polymer-coated albumin microspheres as carriers for intravascular tumor targeting of cisplatin, *Cancer Chemother. and Pharm.*, 29:117-21; Tabata, et al., 1988, Potentiation of antitumor activity of macrophages by recombinant interferon alpha A/D contained in gelatin microspheres, *Jpn. J. Cancer Res.*, 79:636-646), polysaccharides (Rongved, et al., 1991, Crossed-linked, degradable starch microspheres as carriers of paramagnetic resonance imaging: synthesis, degradation, and relaxation properties, *Carbohydrate Res.*, 145:83-92; Carter, et al., 1991, The combination of degradable starch microspheres and angiotensin II in the manipulation of drug delivery in an animal model of colorectal metastasis, *British J. Cancer*, 65:37-9), and synthetic polymers (Davis, et al., 1984, *Microspheres and Drug Therapy*, Amsterdam; Eldridge, et al., 1991, Biodegradable microspheres as a vaccine delivery system, *Molec. Immunology*, 28:287-94; Pappo, et al., 1991, Monoclonal antibody-directed targeting of fluorescent polystyrene microspheres to Peyer's patch M cells, *Immunology*, 73:277-80). Polymeric systems share some of the advantages of liposomal systems such as altered pharmacokinetics and biodistribution. While liposomes might have better prospects of biocompatibility and potential for fusion with cells, polymeric microspheres have more controllable

release kinetics, better stability in storage, and higher drug-loading levels for some classes of compounds.

We have previously synthesized microspheres by the complex coacervation of gelatin and chondroitin sulfate (Truong, et al., 1993, A target-specific microspheres drug delivery system made of enzymatically degradable gelatin and chondroitin sulfate coacervates, *Controlled Release Society*, Abstract #1336; Azhari, et al., 1991, Protein release from enzymatically degradable chondroitin sulfate/gelatin microspheres, *Intern. Symp. Control. Rel. Bioact. Mater.*, 18). These microspheres could be stabilized by cross-linking with glutaraldehyde, the extent of which controls the degradation and drug release rate. Biodegradability of these microspheres in serum is effected by presence of metalloproteinases such as gelatinase, collagenase, and trypsin.

Thus there is a need in the art for a targeted DNA delivery system which can provide controlled release, is simple to make, is stable, is cost effective, has a high DNA loading level, and is relatively non-immunogenic.

#### SUMMARY OF THE INVENTION

It is an object of the invention to provide polymeric particles for delivery of DNA to cells.

It is an object of the invention to provide a method of making polymeric particles for delivery of DNA to cells.

It is another object of the invention to provide a method of delivering DNA to cells using polymeric particles.

These and other objects of the invention are provided by one or more of the embodiments described below. In one embodiment a microparticle for gene

delivery to specific targets is provided. The microparticle comprises gelatin and DNA, and a linking molecule or a targeting ligand is attached to the surface of said microparticle.

In another embodiment of the invention a method of forming microparticles for gene delivery to specific targets is provided. The method comprises the steps of: forming microparticles by coacervation of DNA and gelatin; and adhering a linking molecule or a targeting ligand to the surface of the microparticles.

In yet another embodiment of the invention a method for introducing genes into cells is provided. The method comprises incubating cells to be transfected with solid microparticles comprising gelatin and DNA, wherein a targeting ligand is attached to said microparticle's surface, said targeting ligand binding to the surface of said cells.

Thus the present invention provides the art with an attractive DNA delivery system which is simple to prepare, is cost effective, has controlled release ability, is storage stable, and is biocompatible.

#### BRIEF DESCRIPTION OF THE DRAWINGS

- Figure 1. Schematic diagram showing the synthesis of gelatin-DNA coacervates.
- Figure 2. Gel electrophoresis of cDNA before and after encapsulation. (std = standard; Sup = supernatant, Pellet = microparticles pelleted by centrifugation).
- Figure 3. Controlled release of intact LAMP-1 cDNA was demonstrated *in vitro*. The microparticles were cross-linked with glutaraldehyde at various glutaraldehyde concentrations then degraded with trypsin.

-5-

Figure 3A shows the time course of DNA release at various glutaraldehyde-cross-linking levels. Figure 3B shows (on gels and densitometer tracing) the DNA which was released from the microparticles at various times and at various levels of glutaraldehyde-cross-linking.

Figure 4. Fluorescent images of U937 cells transfected by controls and LAMP-1 cDNA-loaded microparticles (at day 3 post-transfection). Figure 4A: anti-DC44 microparticles without cDNA; Figure 4B: calcium phosphate transfection; Figure 4C: LAMP-1 microparticles without antibody; Figure 4D: LAMP-1 microparticles coated with anti-CD-44 mAB. LAMP-1 expression is manifested as granules (in lysosomes) in the cells.

Figure 5. Flow cytometric analysis of the transfection efficiency of U937 cells by antilymphocyte function associated antigen-1 coated microparticles and controls. The actual mean fluorescence intensity (MFI) is shown in the insert. Msp= microspheres, MRK= a mismatched anti-P-glycoprotein antibody, PLM=anti-LFA antibody.

Figure 6. Temporal expression of LAMP-1 in 293s cells transfected by anti-CD44 coated microparticles.

#### DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

It is a discovery of the present invention that nucleic acid molecules of various chain lengths can complex with polymeric cations in aqueous conditions to form solid microparticles ranging from submicron to microns in size. These



-6-

nucleic acid-loaded microparticles, when appropriately targeted, can transfect cells with phagocytic activity. The rate of microparticle degradation and nucleic acid release can be designed *a priori* by varying the extent of cross-linking. The loading level of nucleic acid can be as high as 30% (w/w), with an encapsulation efficiency of >95%.

According to the present invention, gelatin or other polymeric cation having a similar charge density to gelatin, is used to complex with nucleic acids to form microparticles. The source of gelatin is not thought to be critical; it can be from bovine, porcine, human, or other animal source. Typically the polymeric cation has a molecular weight of between 19,000-30,000. Poly-L-lysine may be particularly useful as the polymeric cation of the present invention. Desirably sodium sulfate is used to induce the coacervation of polymeric cation and nucleic acids. Ethanol can also be used at a concentration of about 40 to 60% to induce coacervation. Chondroitin sulfate can also be incorporated into the microparticle, which is especially beneficial if one desires other substances such as drugs to be incorporated in the microparticle. Typically the concentration of chondroitin sulfate is between about 0.005% and 0.1%.

Targeting ligands can be directly bound to the surface of the microparticle or can be indirectly attached using a "bridge" or "spacer". Because of the amino groups provided by the lysine groups of the gelatin, the surface of the microparticles can be easily derivatized for the direct coupling of targeting moieties. Alternatively, spacers (linking molecules and derivatizing moieties on targeting ligands) such as avidin-biotin can be used to indirectly couple targeting ligands to the microparticles. Biotinylated antibodies and/or other biotinylated

-7-

ligands can be coupled to the avidin-coated microparticle surface efficiently because of the high affinity of biotin ( $K_d \sim 10^{15} \text{ M}^{-1}$ ) for avidin (Hazuda, et al., 1990, Processing of precursor interleukin 1 beta and inflammatory disease, *J. Biol. Chem.*, 265:6318-22; Wilchek, et al., 1990, Introduction to avidin-biotin technology, *Methods In Enzymology*, 184:5-13). Orientation-selective attachment of IgGs can be achieved by biotinylating the antibody at the oligosaccharide groups found on the  $F_C$  portion (O'Shannessy, et al., 1984, A novel procedure for labeling immunoglobulins by conjugation to oligosaccharides moieties, *Immunol. Lett.*, 8:273-277). This design helps to preserve the total number of available binding sites and renders the attached antibodies less immunogenic to  $F_C$  receptor-bearing cells such as macrophages. Spacers other than the avidin biotin bridge can also be used, as are known in the art. For example, Staphylococcal protein A can be coated on the microparticles for binding the  $F_C$  portions of immunoglobulin molecules to the microparticles.

Cross-linking of linking molecules or targeting ligands to the microparticle is used to promote the stability of the microparticle as well as to covalently affix the linking molecule or targeting ligand to the microparticle. The degree of cross-linking directly affects the rate of nucleic acids release from the microshperes. Cross-linking can be accomplished using glutaraldehyde, carbodiimides such as EDC (1-ethyl-3-(3-dimethylaminopropyl)-carbodiimide, DCC (N,N'-dicyclohexylcarbodiimide), carboxyls (peptide bond) linkage, bis(sulfosuccinimidyl) suberate, dimethylsuberimidate, etc.

Targeting ligands according to the present invention are any molecules which bind to specific types of cells in the body. These may be any type of

molecule for which a cellular receptor exists. Preferably the cellular receptors are expressed on specific cell types only. Examples of targeting ligands which may be used are hormones, antibodies, cell-adhesion molecules, saccharides, drugs, and neurotransmitters.

The microparticles of the present invention have good loading properties. Typically, following the method of the present invention, microparticles having at least 5% (w/w) nucleic acids can be achieved. Preferably the loading is greater than 10 or 15% nucleic acids. Often microparticles of greater than 20 or 30% nucleic acids can be achieved. Typically loading efficiencies of nucleic acids into microparticles of greater than 95% can be achieved.

The method of the present invention involves the coacervation of polymeric cations and nucleic acids. Because this process depends on the interaction of the positively charged polymeric cations and the negatively charged nucleic acids it can be considered as a complex coacervation process. However, sodium sulfate (or ethanol) induces the coacervation reaction by inducing a phase transition, and therefore it could also be considered as a simple coacervation reaction. Nucleic acids are present in the coacervation mixture at a concentration of between 1 ng/ml to 500  $\mu$ g/ml. Desirably the nucleic acids are at least about 2-3 kb in length. Sodium sulfate is present at between 7 and 43 mM. Gelatin or other polymeric cation is present at between about 2 and 7% in the coacervation mixture.

An attractive microparticle delivery system requires a delicate balance among factors such as the simplicity of preparation, cost effectiveness, nucleic acids loading level, controlled release ability, storage stability, and immunogenicity of the components. The gene delivery system described here may offer advantages

compared to other particulate delivery systems, including the liposomal system. The problems of instability, low loading level, and controlled release ability are better resolved with the polymeric microparticle systems. Gelatin has received increasing biologic use ranging from surgical tissue adhesive (Weinschelbaum, et al., 1992, Surgical treatment of acute type A dissecting aneurysm with preservation of the native aortic valve and use of biologic glue. Follow-up to 6 years, *J. Thorac. Cardiovasc. Surg.*, 130:369-74) to quantitative immunohistochemical assays (Izumi, et al., 1990, Novel gelatin particle agglutination test for serodiagnosis of leprosy in the field, *J. Clinical Microbiol.*, 28:525-9) and as drug delivery vehicle (Tabata, et al., 1991, Effects of recombinant alpha-interferon-gelatin conjugate on in vivo murine tumor cell growth, *Cancer Res.*, 51:5532-8), due to its biocompatibility and enzymatic degradability *in vivo*. Compared to other synthetic polymeric systems, such as the extensively studied polylactic/polyglycolic copolymers, the mild conditions of microparticle formulation are appealing. Unlike the solvent evaporation and hot-melt techniques used to formulate synthetic polymeric microparticles, complex coacervation requires neither contact with organic solvents nor heat. It is also particularly suitable for encapsulating bio-macromolecules such as nucleic acids not only through passive solvent capturing but also by direct charge-charge interactions.

Unlike viral vectors, which cannot deliver genes larger than 10 kb, the microparticle delivery system of the present invention does not have such size limitations. Nucleic acid molecules of greater than about 2 kb can be used, and nucleic acid molecules even greater than 10 kb may be used.

-10-

In general, the range of possible targets is dependent on the route of injection e.g. intravenous or intraarterial, subcutaneous, intra-peritoneal, intrathecal, etc. For systemic injections, the specificity of this delivery system is affected by the accessibility of the target to blood borne microparticles, which in turn, is affected by the size range of the particles. Size of the particles is affected by temperature, component concentration, and pH in the coacervation mixture. The particles can also be size-fractionated, e.g., by sucrose gradient ultracentrifugation. Particles with size less than 150 nanometers can access the interstitial space by traversing through the fenestrations that line most blood vessels walls. Under such circumstances, the range of cells that can be targeted is extensive. An abbreviated list of cells that can be targeted includes the parenchymal cells of the liver sinusoids, the fibroblasts of the connective tissues, the cells in the Islets of Langerhans in the pancreas, the cardiac myocytes, the Chief and parietal cells of the intestine, osteocytes and chondrocytes in the bone, keratinocytes, nerve cells of the peripheral nervous system, epithelial cells of the kidney and lung, Sertoli cells of the testis, etc. The targets for particles with sizes greater than 0.2 microns will be confined largely to the vascular compartment. Here, the targetable cell types include erythrocytes, leukocytes (i.e. monocytes, macrophages, B and T lymphocytes, neutrophils, natural killer cells, progenitor cells, mast cells, eosinophils), platelets, and endothelial cells.

For subcutaneous injections, the targetable cells includes all cells that resides in the connective tissue (e.g. fibroblasts, mast cells, etc.), Langerhans cells, keratinocytes, and muscle cells. For intrathecal injections, the targetable cells include neurons, glial cells, astrocytes, and blood-brain barrier endothelial

cells. For intraperitoneal injection, the targetable cells include the macrophages and neutrophil.

**Examples:**

*Matrix Materials:* Gelatin (60 bloom, type A from porcine skin), chondroitin 4-sulfate, glutaraldehyde (25%, grade 1), 1-ethyl-3-(3-dimethylaminopropyl)-carbodiimidehydrochloride (EDC hydrochloride), and ultra-pure sucrose were purchased from Sigma Chemical Co. (St. Louis, MO). Biotin LC hydrazide, and NeutrAvidin, and Coomassie protein assay reagents were from Pierce (Rockford, IL). Centricon microconcentrators were from Amicon (Beverly, MA).

*Monoclonal antibodies:* mAb PLM-2, a BALB/c mouse anti-porcine LFA-1 (IgG<sub>1b</sub>) which also cross reacts with murine LFA-1, was isolated and purified as previously described (Hildreth, et al., 1989, Monoclonal antibodies against porcine LFA-1: species cross-reactivity and functional effects of b-subunit-specific antibodies, *Molec. Immunol.*, 26:883-895). IB-4B, a rat anti-mouse LAMP-1 ascite fluid and a mouse anti-human CD44 mAb were isolated as previously described (de Wet, et al., 1987, Firefly luciferase gene: structure and expression in mammalian cells, *Mol. & Cell. Biol.*, 7:725-37). CHA is a IgG<sub>1</sub> that does not recognize any known *in vivo* mouse epitopes (Hybritech Inc., San Diego, CA). Affinity-purified FITC and Texas Red-labeled polyclonal anti-rat IgGs were obtained from Sigma.

-12-

**Genes:** Two genes were used to demonstrate the feasibility of this delivery system. The LAMP-a cDNA is a 6.4 kb circular supercoiled plasmid cDNA with a mouse LAMP-1 gene (2.4 kb) inserted into an Invitrogen plasmid cDNA with a CMV promoter (Guzmanieri, et al., 1993, *J. Biol. Chem.*, 268:1941). Detection of LAMP-1 expression was done by staining cells with anti-LAMP-1 mAb and with secondary anti-IgG mAb conjugated with Texas Red. The gene coding for luciferase enzyme is widely used in cell biology for the study of gene expression because of the high sensitivity of the assay, its simplicity, and low cost. In addition, the enzyme is a good reporter of gene expression because it is a cytosolic protein that does not require post-translational processing for enzymatic activity (de Wet, et al., 1987, Firefly luciferase gene: structure and expression in mammalian cells, *Mol. & Cell. Biol.*, 7:725-37; Wood, et al., 1989, Introduction to beetle luciferases and their applications, *J. of Biolumin. & Chemilum.*, 4:289-301). The presence of luciferase can be readily detected by an enzymatic reaction that involve the oxidation of beetle luciferin with concomitant production of a photon (in the form of chemiluminescence.) The assay was carried out using an assay kit purchased from Promega Corp. (Madison, WI).

**Synthesis of microspheres:** A detailed schematic diagram for the synthesis of the gelatin-DNA coacervates is shown in Figure 1. All concentrations described are final concentrations in the reaction mixture set at 67°C unless otherwise stated. Gelatin/plasmid DNA microparticles coated with avidin were synthesized by first preparing a 3.5 mg/ml solution of plasmid DNA encoding a lysosomal associated membrane protein-1 (LAMP-1) (6.7 Kb, circular supercoiled) in 42 mM sodium sulfate ( $\text{Na}_2\text{SO}_4$ ). Coacervation was initiated by the addition of gelatin (5%) to

-13-

the DNA/ $\text{Na}_2\text{SO}_4$  solution at equal volume while vortexing at high speed for 1 minute. Coencapsulation of drugs and other agents can be achieved by adding directly to the DNA/ $\text{Na}_2\text{SO}_4$  solution before initiating coacervation with gelatin. Avidin (5 mg/ml) was added to the microsphere suspension at a final concentration of 75 ug avidin/ml microsphere solution. The microspheres mixture was layered onto a layer of 70% sucrose (w/v) and centrifuged at 6,000 x g for 4 minutes (Brinkman Instruments Inc., Westbury, NY, model L8-75). Microsphere fractions recovered from the sucrose layer was diluted 5-fold with water then cross-linked with glutaraldehyde (12.5 mM final concentration) for 10 minutes at room temperature. Unreacted glutaraldehyde was quenched by adding ethanolamine (1 M) for 10 minutes. The microspheres were dialyzed by sucrose centrifugation as described above.

*Attachment of biotinylated mAbs to avidin-coated microspheres:* 30 ug of antibodies (biotinylated according to established procedures (O'Shannessy, et al., 1984, A novel procedure for labeling immunoglobulins by conjugation to oligosaccharides moieties, *Immunol. Lett.*, 8:273-277)) was added to 1 ml of avidin-coated microspheres suspension (11 mg/ml) for 1 hour with gentle agitation. Unbound mAb was removed from microspheres by dialysis.

*Characterization of microsphere and binding performance:* DNA loaded microspheres exhibited polymorphic colloid shape with a polydispersed particle size of less than 3 microns as determined by light microscopy. Purified microspheres were stable for at least one month without appreciable degradation. The loading level for LAMP-1 plasmid DNA was 20% (w/w). The encapsulation efficiency was typically >95%. The mobility of the free LAMP-1 DNA and the



-14-

released DNA (from the microsphere) in 1% agarose gel electrophoresis were identical (Fig. 2), suggesting that the encapsulated DNA was released in its original form. Release rate of the cDNA from the microspheres was dependent on the crosslinking density and on the enzyme level (Figure 4). Sustained release of up to weeks can be readily obtained.

We tested the ability of the LAMP-1 DNA loaded microspheres to bind and subsequently transfect a human histiocytic lymphoma cell line (U937) in tissue culture. When coated with either anti-LFA or anti-CD44 monoclonal antibody (both protein targets were expressed in high amount of U937 cell surface), expression LAMP-1 protein was detected by day 3 (Fig. 4A, fluorescent granules) when stained with antibodies recognizing LAMP-1. The staining pattern of U937 cells incubated with LAMP-1 microspheres was identical to the calcium phosphate method of transfection (Figure 4B). Microspheres that were either coated with avidin or non-specific CHA mAb showed no granular staining patterns, and were identical to untreated cells (Fig. 4C).

Using flow cytometry, we showed that the expression of LAMP-1 was detected in up to 5% of U937 cells in culture (Figure 5). None of the controls -- blank microspheres, microspheres with cDNA but no antibodies, microspheres with cDNA and coated with a mismatched anti-P-glycoprotein antibody (MRK-Msp.), and free cDNA at a concentration six time higher than entrapped in the microspheres -- showed any evidence of transfection. The efficiency of transfection appears to be dose-responsive. In general, the transfection efficiency of this particular gene and cell type is comparable between the proposed microspheric delivery system (1-10%) and the calcium phosphate precipitation

-15-

method (2-15%). Figure 6 demonstrates the concept in a different cell type using a different monoclonal antibody. Again, free cDNA could not transfect the cells. Eventually the LAMP-1 expression disappeared after several passages. Positive results were also obtained for the luciferase reporter gene system. Transfection was clearly detected by measurement of luciferase enzymatic activity, in 293s cells incubated with luciferase gene-loaded microspheres.

CLAIMS

1. A solid microparticle for gene delivery to specific target cells, comprising a polymeric cation and nucleic acids, wherein a linking molecule or a targeting ligand is attached to the surface of said microparticle.
2. The microparticle of claim 1 wherein the linking molecule is attached to said microparticle.
3. The microparticle of claim 1 wherein the targeting ligand is attached to said microparticle.
4. The microparticle of claim 2 wherein the linking molecule is covalently attached to said microparticle by means of glutaraldehyde cross-linking.
5. The microparticle of claim 2 wherein said linking molecule is avidin.
6. The microparticle of claim 2 wherein a targeting ligand is coupled to the linking molecule.
7. The microparticle of claim 3 wherein said targeting ligand is selected from the group consisting of hormones, antibodies, cell-adhesion molecules, saccharides, drugs, and neurotransmitters.
8. The microparticle of claim 6 wherein said targeting ligand is selected from the group consisting of hormones, antibodies, cell-adhesion molecules, saccharides, drugs, and neurotransmitters.
9. The microparticle of claim 1 wherein said polymeric cation is gelatin.

10. The microparticle of claim 1 wherein said microparticle comprises greater than 5% (w/w) nucleic acids.

11. The microparticle of claim 1 wherein said microparticle comprises greater than 20% (w/w) nucleic acids.

12. The microparticle of claim 5 wherein a biotinylated targeting ligand is coupled to the linking molecule.

13. The microparticle of claim 12 wherein the biotinylated targeting ligand is a biotinylated antibody.

14. The microparticle of claim 13 wherein biotin is bound to said antibody at oligosaccharide groups on the F<sub>c</sub> portion of said antibody.

15. The microparticle of claim 1 wherein said nucleic acids comprises a gene larger than 10 kb.

16. The microparticle of claim 1 further comprising chondroitin sulfate.

17. A method of forming solid microparticles for gene delivery to specific target cells, comprising the steps of:

forming microparticles by coacervation of nucleic acids and a polymeric cation;

adhering a linking molecule or a targeting ligand to the surface of the microparticles.

18. The method of claim 17 further comprising the step of:

cross-linking the linking molecule or the targeting ligand to the microparticles.

19. The method of claim 17 wherein a linking molecule is adhered, said method further comprising the step of:

binding a targeting ligand to the linking molecule.

20. The method of claim 17 wherein the coacervation is performed in the presence of sodium sulfate.
21. The method of claim 17 wherein the polymeric cation is gelatin.
22. The method of claim 17 wherein a targeting ligand is adhered to the surface of said microparticle, said targeting ligand being selected from the group consisting of antibodies, hormones, cell-adhesion molecules, saccharides, drugs, and neurotransmitters.
23. The method of claim 19 wherein the targeting ligand is selected from the group consisting of antibodies, hormones, cell-adhesion molecules, saccharides, drugs, and neurotransmitters.
24. The method of claim 17 wherein the linking molecule is avidin.
25. The method of claim 19 wherein the targeting ligand is derivatized so that it binds to the linking molecule.
26. The method of claim 21 wherein the gelatin is present at a concentration of about 2-7% in the step of coacervation.
27. The method of claim 17 wherein the nucleic acids are present in a concentration of 1 ng/ml to 500  $\mu$ g/ml in the step of coacervation.
28. The method of claim 20 wherein the concentration of sodium sulfate is between about 7 and 43 mM in the step of coacervation.
29. A method for introducing genes into cells, comprising the steps of:  
incubating (a) cells to be transfected with (b) solid microparticles comprising polymeric cations and nucleic acids, wherein a targeting ligand is

attached to said microparticle's surface, said targeting ligand binding to the surface of said cells to be transfected.

30. The method of claim 29 wherein the targeting ligand is attached to said microparticle's surface by means of a linking molecule.

31. The method of claim 29 wherein the linking molecule is avidin.

32. The method of claim 29 wherein the targeting ligand is selected from the group consisting of: antibodies, hormones, cell-adhesion molecules, saccharides, drugs, and neurotransmitters.

33. The method of claim 29 wherein the polymeric cation is gelatin.

34. The method of claim 29 wherein the nucleic acid is DNA.

35. The method of claim 29 wherein the nucleic acid is RNA.




FIG. 1


\* Circular, supercoiled double stranded plasmid cDNA 6.8kb (LAMP-1)  
or ~5.1kb (Luciferase) 0.6-3.5 mg/ml in H<sub>2</sub>O.

\*\* gelatin (60 bloom, Type A from porcine skin) freshly made.

2 / 8

## FIG. 2

LAMP-1	Mosp	LAMP-1	Mosp
std	Rx	std	Rx
(0.5ug)	Sup	(1.5ug)	Pellet




SUBSTITUTE SHEET (RULE 26)



3 / 8

FIG. 3A






FIG. 3B

5 / 8

FIG. 4A





FIG. 4B



6/8

FIG. 4C






FIG. 4D




SUBSTITUTE SHEET (RULE 26)

7/8



8/8

FIG. 6



## INTERNATIONAL SEARCH REPORT

Intern. Application No.  
PCT/US 95/07857

A. CLASSIFICATION OF SUBJECT MATTER IPC 6 C12N15/87 C12N15/88 A61K9/50		
According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) IPC 6 C12N A61K		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the international search (name of data base and, where practical, search terms used)		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	<p>PROC. INT. SYMP. CONTROLLED RELEASE BIOACT. MATER., 20TH (1993), 474-5. EDITOR(S): ROSEMAN, THEODORE J.; PEPPAS, NICHOLAS A.; GABELNICK, HENRY L. PUBLISHER: CONTROLLED RELEASE SOC., DEERFIELD, ILL. CODEN: 59LOAL, 25 - 30 July 1993 TRUONG, VU. L. ET AL 'A target-specific microspheres drug delivery system made of enzymically degradable gelatin and chondroitin sulfate coacervates' cited in the application see page 474, left column, line 1 - page 475, right column, paragraph 4; figures 1-4</p> <p style="text-align: center;">--- -/--</p>	1-35
<input checked="" type="checkbox"/> Further documents are listed in the continuation of box C. <input checked="" type="checkbox"/> Patent family members are listed in annex.		
* Special categories of cited documents: "A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier document but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. "&" document member of the same patent family		
Date of the actual completion of the international search  30 October 1995		Date of mailing of the international search report  05.12.95
Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl, Fax (+ 31-70) 340-3016		Authorized officer  Hornig, H

## INTERNATIONAL SEARCH REPORT

International Application No.

PCT/US 95/07857

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	<p>INT. J. PHARM. (1994), 105(2), 181-6            CODEN: IJPHDE; ISSN: 0378-5173,            1994            CORTESI, RITA ET AL. 'Gelatin microspheres            as a new approach for the controlled            delivery of synthetic oligonucleotides and            PCR-generated DNA fragments'            the whole document</p>	1-35
Y	<p>PROC. PROGRAM INT. SYMP. CONTROLLED            RELEASE BIOACT. MATER., 18TH (1991),            617-18. EDITOR(S): KELLAWAY, IAN W.            PUBLISHER: CONTROLLED RELEASE SOC.,            DEERFIELD, ILL. CODEN: 58GMAH,            8 - 11 July 1991            AZHARI, ROSA ET AL. 'Protein release from            enzymically-degradable chondroitin            sulfate/ gelatin microspheres'            cited in the application            see page 617, line 1 - page 618, line 29;            figures 1,2</p>	1-35
Y	<p>CANCER RESEARCH,            vol. 53, no. 24, 15 December 1993 AACR,            BALTIMORE, US,            pages 5841-5844,            P.T. GOLUMBEK ET AL. 'Controlled release,            biodegradable cytokine depots: A new            approach in cancer vaccine design'            see page 5841, right column, line 17 -            line 33</p>	1-35
Y	<p>J. IMMUNOL. METHODS,            vol. 132, 1990 ELSEVIER, AMSTERDAM NL,            pages 25-35,            H.C. LOUGHREY ET AL. 'Optimized            procedures for the coupling of proteins to            liposomes'            the whole document</p>	1-35
Y	<p>J. BIOL. CHEM.,            vol. 264, no. 29, 15 October 1989 AM. SOC.            BIOCHEM. MOL. BIOL., INC., BALTIMORE, US,            pages 16985-16987,            C.H. WU ET AL. 'Targeting genes: Delivery            and persistent expression of a foreign            gene driven by mammalian regulatory            elements in vivo'            the whole document</p>	1-35
Y	<p>EP, A, 0 544 292 (BOEHRINGER MANNHEIM GMBH)            2 June 1993            see page 2, line 14 - page 4, line 39;            claims 1-11</p>	1-35

-/--



# INTERNATIONAL SEARCH REPORT

International Application No  
PCT/US 95/07857

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	EP,A,0 388 758 (BOEHRINGER INGELHEIM INT) 26 September 1990 see page 2, line 37 - page 6, line 8; claims 1-17 ---	1-35
A	PROC. INT. SYMP. CONTROLLED RELEASE BIOACT. MATER., 19TH (1992), 152-3. EDITOR(S): KOPECEK, JINDRICH. PUBLISHER: CONTROLLED RELEASE SOC., DEERFIELD, ILL. CODEN: 58JTAJ, 1992 AZHAKI, R. ET AL 'Enzymically-triggered release of recombinant soluble complement receptor 1 (sCR1) from chondroitin sulfate/ gelatin microspheres' the whole document ---	1-35
A	EP,A,0 030 885 (PASTEUR INSTITUT ;INST TECH SURFACES ACTIVES (FR)) 24 June 1981 the whole document ---	1-35
A	J. MICROENCAPSULATION, vol. 11; no. 3, May 1994 - June 1994 TAYLOR & FRANCIS LTD., PHILADELPHIA, PA, US, pages 249-260, C. NASTRUZZI ET AL. 'Production and in vitro evaluation of gelatin microspheres containing an antitumour tetra-amidine' the whole document ---	1-35
P,Y	WO,A,95 03789 (JOHNS HOPKINS UNIVERSITY SCHOO) 9 February 1995 the whole document -----	1-35

# INTERNATIONAL SEARCH REPORT

International Application No  
PCT/US 95/07857

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-0544292	02-06-93	DE-A- 4139001 JP-A- 6303987	03-06-93 01-11-94
EP-A-0388758	26-09-90	AU-B- 637085 AU-B- 5137290 CA-A- 2012311 JP-A- 3200800 US-A- 5354844	20-05-93 20-09-90 16-09-90 02-09-91 11-10-94
EP-A-0030805	24-06-81	FR-A- 2470794 CA-A- 1167398 JP-A- 56035196 US-A- 4373027	12-06-81 15-05-84 01-08-81 08-02-83
WO-A-9503789	09-02-95	AU-B- 7208494	28-02-95